



SUTHERLAND SUTHERLAND EGGSHELL ENAMEL

PRODUCT DESCRIPTION

A quality alkyd-based Sutherland Eggshell enamel paint.

PRODUCT FEATURES

Dries to a tough durable finish with good weather resistance. Suitable as a decorative & protective finish for both interior & exterior, steel, timber & masonry substrates.

TECHNICAL INFORMATION

Colour:	White
Appearance:	Eggshell surface finish
Generic type:	Medium oil alkyd
Total solids:	65 - 68%
Volume solids:	±40%
Viscosity:	78Ku
Spreading rate:	8 - 10m ² /litre
Solvent:	Mineral Turpentine
DFT:	25 - 35µm
Mix ratio:	Single pack ready for use
Packaging:	1, 5 & 20 litre

SURFACE PREPARATION

All surfaces are to be clean, dry & free from loose paint, oil, grease & other contaminants. Rusted metal must be treated & primed prior to application of Sutherland Eggshell Enamel. Sutherland Eggshell Enamel is designed as final coat, thereafter, ensure substrates are primed & undercoated prior to application of Sutherland Eggshell Enamel. Old enamel surfaces should be thoroughly degreased with Sugarsoap, abraded & dust free prior to application of Sutherland Eggshell Enamel.

APPLICATION

Sutherland Eggshell Enamel is to be applied to correctly prepared Surfaces, e.g.

Wood:	White Wood Primer Knott Sealer Universal Undercoat Sutherland Eggshell Enamel
Masonry:	Bonding Liquid or Masonry Primer Universal Undercoat Sutherland Eggshell Enamel
Steel:	Etch Primer Universal Undercoat Sutherland Eggshell Enamel
Airless spray:	No dilution necessary Nozzle pressure: 100 - 120 bar Nozzle orifice: 0.015"

Conventional spray: 20 - 25% dilution recommended (Use Mineral Turpentine)

Air pressure: 2 - 3 bar
Nozzle orifice: 1.5 - 2mm
Brush and Roller: 10% dilution if needed.
Clean up: Mineral Turpentine for dilution & clean up

ENVIRONMENT

It is recommended that application be confined to the following:

Surface temperature:	Min. 5°C	Max. 45°C
Ambient temperature:	Min. 5°C	Max. 45°C
Relative humidity:	Min. 0%	Max. 85%
	Or at least 3°C > Dew point	

POT LIFE:

Infinite. Air drying after evaporation of thinners. Do not leave container open.

DRYING TIME

The drying time is dependent on temperature & ventilation. The higher the temperature & the better the ventilation, the shorter the touch dry & hard dry times.

<i>Substrate Temperature</i>	<i>Touch Dry</i>	<i>Hard Dry</i>
25°C	8 hours	16 hours

OVERCOATING TIMES

10°C:	48 hours
15°C:	24 hours
20°C:	16 hours
25°C:	8 hours

All the above are given as guidelines & can not be assumed to be absolute, as variances will result from different film thickness, environment & temperature.

STORAGE AND HANDLING

Store away from direct sunlight, open flames & severe cold.
Shelf life: 1 year in original sealed containers.
Flash point: 24°C

LIMITATIONS

Applications more than 40 µm DFT should be avoided to prevent wrinkling.

SAFETY PRECAUTIONS

Work with PVC gloves, safety glasses & ensure good ventilation. When spraying with Sutherland Eggshell Enamel, work in a well-ventilated area & wear a suitable respirator. This product contains flammable materials. Keep away from sparks & open flames & no smoking should be permitted in the area.

KEEP OUT OF REACH OF CHILDREN.

Information Provided is based on Laboratory evaluations and data believed to be reliable.
Recommendations are given in good faith but without warranty. It is the user's responsibility to determine the suitability for their own use.
It is not to be considered a guarantee of the products properties.

For more information contact our Factories:
Western Cape: Tel/Fax: (021) 853-8105 Mpumalanga: Tel: (013) 246-2570 Fax: (013) 246-2573